

NF A49-111-78 STEEL TUBES PLAIN END SEAMLESS TUBES OF COMMERCIAL QUALITY FOR GENERAL PURPOSES AT MEDIUM PRESSURE

1. Chemical Composition

Grade	Mfg. Process	Chemical Composition (%)								
		C	Si	Mn	P	S	Ni	Cr	Mo	Others
TU37a	S	0.24Max	-	1.30Max	0.05Max	0.05Max	-	-	-	-

2. Mechanical Properties

Grade	Tensile Test MPa or N/mm ²	
	Min Yield point	Tensile Strength
TU37a	210	360Min