

NF A49-210-85 STEEL TUBES SEAMLESS COLD DRAWN TUBES FOR FLUID PIPING

1. Chemical Composition

Grade	Mfg. Process	Chemical Composition (%)								
		C	Si	Mn	P	S	Ni	Cr	Mo	Others
TU37B	S	0.18Max	0.35Max	0.75Max	0.040Max	0.045Max	-	-	-	-
TU42B	S	0.22Max	0.35Max	0.75Max	0.040Max	0.045Max	-	-	-	-

2. Mechanical Properties

Grade	Tensile Test MPa or N/mm ²		Remarks
	Min Yield point	Tensile Strength	
TU37B	220	360~480	(STS370)
TU42B	235	410~530	(STS410)

JIS Number and Corresponding Foreign Standards

[illegible]